

PTFE

Tubo flessibile

Linear flexible hose

CARATTERISTICHE

I fluoropolimeri sono conosciuti per le eccellenti performance in numerose applicazioni critiche.

- ha un'ottima resistenza ai prodotti chimici
- è estremamente stabile fino a 260°C (500°F)
- ha ottime proprietà dielettriche
- rimane inalterato a contatto con ossigeno, ozono e raggi UV
- ha il coefficiente di frizione più basso fra tutti i polimeri
- ignifugo UL94 V0

CHARACTERISTICS

Fluoropolymer materials are known for their outstanding properties under a variety of applications.

- offers excellent resistance to chemical products
- is extremely inert and is stable up to a temperature of 260°C (500°F)
- has almost ideal dielectric properties
- is virtually unaffected by oxygen, ozone and UV rays
- has the lowest coefficient of friction of all polymers
- fireproof to UL94 V0

TEMPERATURA °C

PTFE può essere impiegato in una gamma di temperature variante da -60°C a +260°C. Qui di seguito riportiamo una tabella delle pressioni espresse in % in funzione delle temperature.

20°	50°	100°	150°	200°
100%	50%	35%	30%	10%

TEMPERATURE °C

PTFE can be used in a range of temperatures from -60°C to + 260°C. The table here below shows pressure values expressed as a % in relation to temperature.

APPLICAZIONI

Il PTFE è utilizzato quando temperature estreme vengono abbinate ad ambienti di lavoro aggressivi e critici.

APPLICATIONS

PTFE is used when high temperatures are combined with aggressive and critical workplace environments.

RACCORDI CONSIGLIATI

Si consiglia l'utilizzo con raccordi a calzamento. Su richiesta disponibile PTFE a tolleranze ridotte per utilizzo con raccordi rapidi.

SUGGESTED FITTINGS

Suitable to use with swivelling fittings. Available on demand PTFE hoses with reduced tolerances to use with push-in fittings.



Cod.	Ø int.	Tolleranze	Parete	Tolleranze	Ø est.	Peso	Raggio	Pressioni a 23°C - Pressure at 23°C	
	I.D.	Tol	Wall	Tol	O.D.	Weight	Bending radius	ATM	
	mm		mm		mm	gr/m	mm	scoppio-burst	esercizio-working
PTFE 1,6x3,17	1,6	± 0,16	0,785	± 0,15	3,17	± 13	13	64	21
PTFE 2x4	2	± 0,16	1	± 0,15	4	± 20	20	60	20
PTFE 2,5x4	2,5	± 0,16	0,75	± 0,15	4	± 16	21	40	13
PTFE 3x5	3	± 0,20	1	± 0,15	5	± 27	25	48	16
PTFE 3,18x6,35	3,18	± 0,20	1,585	± 0,20	6,35	± 51	26	60	20
PTFE 4x6	4	± 0,20	1	± 0,15	6	± 34	35	40	13
PTFE 6x8	6	± 0,25	1	± 0,15	8	± 47	65	30	10
PTFE 6x10	6	± 0,25	2	± 0,20	10	± 108	50	48	16
PTFE 6,35x9,52	6,35	± 0,25	1,585	± 0,20	9,52	± 84	57	38	13
PTFE 8x10	8	± 0,30	1	± 0,15	10	± 60	100	24	8
PTFE 9x12	9	± 0,30	1,5	± 0,17	12	± 105	100	25	8
PTFE 10x12	10	± 0,30	1	± 0,15	12	± 73	150	20	7
PTFE 12x14	12	± 0,35	1	± 0,15	14	± 86	200	17	6
PTFE 12,5x15	12,5	± 0,35	1,25	± 0,15	15	± 114	200	20	7
PTFE 15x18	15	± 0,35	1,5	± 0,15	18	± 164	250	20	7

SCHEDA TECNICA

DATA SHEET

Proprietà	Unità / Unit	Specifiche / Specification	Valori / Values	Property
Densità	G/cm³	D 792	2,15	Density
Punto di fusione	°C	ISO 3416C	327	Melting point
Assorbimento d'acqua	%	D 570	< 0,01	Water absorption
Costante dielettrica	-	D 150 at 10(10x2) Hz	2,1	Dielectric constant
Fattore di dissipazione dielettrica	-	D 150 at 10(10x2) Hz	0,0002	Dielectric dissipation factor
Resistenza dielettrica (10 mils film)	Volt/mil	D 149	> 1400	Dielectric strenght (10 mils film)
Resistività di volume	Ohm-cm	D 257	> 10(10x17)	Volume resistivity
Modulo a trazione	PSI	D 638	90000	Tensile modulus
Modulo a flessione a 23°C	PSI	D 790	80000	Flexural modulus
Allungamento	%	D 1708 - D 638	300	Elongation
Permeabilità	%	D2863	> 95	Oxygene index
Resistenza alla fiamma	-	UL 94	V0	Flame resistance
Durezza	shore D	D 2240	60	Hardness